

Hot rolled flat steel bars

Business contact

Riva Acciaio - Viale Certosa, 249 - 20151 Milan (Italy) Phone +39 02.30.700 - Fax +39 02.38000.346 Email commerciale.riva@rivagroup.com

Revision 10/2020



Revision: 10/2020 - Page 2 of 5

STEEL RANGE

Structural steels EN 10025-2-3-5

Free cutting non-alloyed steels EN 10087

Case hardening steels EN 10084

Steels for quenching and tempering EN 10083-2-3

Steels for quenched and tempered springs EN 10089

Steels for cold heading and cold extrusion EN 10263

Micro-alloyed steels EN 10267

Steels for pressure purposes EN 10273 - ASTM A105 - ASTM A 350

Note: possibility of supplying steels in accordance with Customer specifications, to be agreed upon at the order stage.

PRODUCTION RANGE

STANDARD MANUFACTURING SIZES

Cerveno: width from 35 to 202 mm with thickness from 7 to 92 mm Sellero: width from 180 to 300 mm with thickness from 20 to 50 mm (See the enclosed shape list - It is advisable to print the whole specific page in "A3 - Actual Size" format).

BAR LENGTH

Cerveno: $3 \div 12.5 \text{ m}$ (including length+ tolerance) Sellero: $5 \div 18.2 \text{ m}$ (including length+ tolerance) Commercial length with range $\le 1 \text{ m}$ Standard Fixed Length -- 0/+200 mm or +/- 100 mm. Extra Standard Fixed Length -- 0/+100 mm or +/- 50 mm. (to be agreed upon)

DIMENSIONAL TOLERANCES: UNI EN 10058; DIN 1017; DIN 59200; NFA 45-001; NFA 45-102

Standard	UNI EN 10058; DIN 1017; DIN 59200; NFA 45-001; NFA 45-102
Extra standard	In accordance with Customer specification, to be evaluated at the order acceptance stage.

Note: tolerances with different deviations (with the same range) may be accepted, on condition that they have been agreed upon at the order acquisition stage.

STRAIGHTNESS	
Standard	Cerveno: 4 ‰ L for cross-section ≤ 1000 mm2 Cerveno: 2.5 ‰ L for cross-section > 1000 mm2 Sellero: 4 ‰ L
Extra Standard	Cerveno: camber ≤ 1,5 ‰ L with straightening
PERPENDICULARITY	
Standard	Thickness ≤ 25 mm. ≤ 0.5 mm Thickness > 25 mm ≤ 40 mm: ≤ 1 mm Thickness > 40 mm ≤ 92 mm: ≤ 1,5 mm
Extra Standard	In accordance with Customer specification, to be evaluated at the order acceptance stage.



Standard

Revision: 10/2020 - Page 3 of 5

END APPEARANCE	
Standard	Cerveno: Hot shear cut with flat blades. Sellero: Cold saw cut at 2 ends.
Extra Standard	Cerveno: Cold saw cut at 1 or 2 ends (to be agreed).
SUPERFICIAL DEFECTS	

Production statistics 0.008 *Side with 0.3 minimum and 0.6 mm maximum.

NON-DESTRUCTIVE TESTS FOR INTE	ERNAL DEFECTS
Standard	Not guaranteed
Extra standard	For ≥ 25 mm thickness: 100% off-line core test \Rightarrow - Manual ultrasonic test with double probe at 90° and H2O coupling. EN 10308 Class 1 - 2 - 3.

Note: the rolled section for 100% testing must be sandblasted in advance and must have a minimum reduction ratio equal to 4:1.

Class B EN 10221

DECARBONISATION	
Standard	Max. 1% of the side, with a minimum equal to 0.30 mm.
Extra standard	In accordance with Customer specification, to be evaluated at the order acceptance stage.

Note: if rolled section subjected to heat treatment, minimum guaranteed decarbonisation is equal to 1.3 mm.

NON-METALLIC INCLUSIONS	
Standard	Macro-purity at ≤ 2 as per S.E.P. 1584 standard, Micro-purity at grade ≤ 2,5 as per ASTM E 45 standard or with K method at the values of the EN 10083/06-1 standard, App E, Macro-segregation ≤ C3-R2-S2 as per ASTM E 381 standard
Extra Standard	Through the vacuum degassing (VD) process it is possible to obtain macro-inclusions falling into grade 0 of the S.E.P. 1584 standard.

BANDING	
Standard	Maximum guaranteed banding as per Grade IV of the UNI 8449 standard.
Extra Standard	Through the vacuum degassing (VD) process, maximum guaranteed banding as per Grade III of the UNI 8449 standard.

AUSTENITE GRAIN REFINING FOR SPECIAL STEELS	
Standard	Guaranteed 5 \div 8 austenite grain as per ASTM E112 or ISO 643. This grain size range is not guaranteed for general purpose structural steels, with the exception of the J2 types envisaged in the EN 10025-2 table.
Extra Standard	With extra standard process, 6 or finer austenite grain can be guaranteed.

MECHANICAL CHARACTERISTICS AND HARDENABILITY	
Standard	In accordance with the standardisation table mentioned in the order. On request, all steels can be produced with hardenability restricted to 2/3 of the H standard band, i.e. in the HL (lower 2/3) and HH (upper 2/3) types. Reference for Jominy test: EN ISO 642 standard.
Extra Standard	In accordance with Customer specification, to be evaluated at the order acceptance stage.



MAGNETIC RETENTIVITY	
Standard	Not guaranteed
Extra Standard	To be evaluated at the order acceptance stage
PACKAGING	
Standard	 4 ÷ 5 Tight containment ties + 2 certified metal lifting rings (Italy) 4 ÷ 5 Tight containment ties 1 Tag per bundle 3 identification stamps per bundle (if requested by the Customer) Colour as requested by the Customer
Extra Standard	Peculiar conditions besides the previous ones, to be evaluated at the order acceptance stage. - 2 Tight containment ties + 4 straps per bundle - 2 tags, 1 at the front and 1 at the rear of the bundle - Polyester lifting belts - Identification stamps on all bars

HEAT TREATMENTS

Our products can be supplied with the following heat treatments:


- Softening annealing +A
 +AC Globular annealing globular level guaranteed ≥ 70%
 Stress-free annealing +SR
 Annealing for ferrite-pearlite structure +FP

- Normalising +N
- Shearability annealing +S Hardening field annealing +TH

ANTI-MIX CHECK	
Standard	Spark test
Extra standard	100% anti-mix check with spectrometer (to be agreed)

BUNDLE WEIGHT	
Standard	2,500 ÷ 3,100 kg
Extra standard	1,500 ÷ 2,000 kg

OTHER INFORMATION							
Cold sawability	Guaranteed						
Cold shearability	Guaranteed with Max. HB = 220						
Manufacturing times	40 ÷ 60 days						
Product certificate	 Compliant with EN 10204 TÜV - AD WO/TRD100 and 97/23/EC Directive (PED) for rolled sections intended for pressurised systems Caterpillar Approval (1E1861) CE certification as per EN 10025-1/06 for rolled sections intended for use in structures 						
Minimum batch size	5 tons for standard products included in the shape list						
Weight tolerance with respect with the ordered amount	 ± 20% up to 5 tons. ± 10% > 5 ÷ 25 tons. ± 6% > 25 tons. 						



67	170	172	175	177	180	182	185	187	190	192	195	197	200	202	Width
															Tnk
															92
															90
															87
															85
															82
															80 77
															75
															72
															70
															67
															65
															62
															60
															57
															55
															52
															50 47
															45
															42
															40
															37
															35
															32
															30
															26,5
															25
															21,5 20
															20 16,5
															16
															15
															13
															12
															11
															10
															9
															8
															7
67	170	172	175	177	180	182	185	187	190	192	195	197	200	202	Width