

Drawn round steel bars

Business contact

Riva Acciaio - Viale Certosa, 249 - 20151 Milan (Italy) **Phone** +39 02.30.700 - **Fax** +39 02.38000.346 **Email** commerciale.riva@rivagroup.com

Revision 07/2019

Drawn round steel bars

Revision: 07/2019 - Page 2 of 4

STEEL RANGE

Structural steels EN 10025-2-3-5

Free cutting non-alloyed steels EN 10087

Case hardening steels EN 10084

Steels for quenching and tempering EN 10083-2-3

Hot-rolled steels for quenched and tempered springs EN 10089

Cold-finished steels EN 10277-2-3-4-5

Steels for cold heading and cold extrusion EN 10263

Micro-alloyed steels EN 10267

Steels for pressure purposes EN 10273 - ASTM A105 - ASTM A 350

Note: possibility of supplying steels in accordance with Customer specifications, to be agreed upon at the order stage.

PRODUCTION RANGE

STANDARD MANUFACTURING SIZES

Drawn round bars: Ø 20 ÷ 120 mm with 0.01 mm progression

BAR LENGTH

 $2.8 \div 6.8 \text{ m} \text{ (including length+ tolerance)}$ Commercial length with range $\leq 1 \text{ m}$ Extra Standard Fixed Length with range -0/+200 mm or $\pm 100 \text{ mm}$ Extra Standard Fixed Length with range $\geq 50 \text{ mm}$

Note: crop end, if agreed upon at the order, \geq 3 m for \leq 10% of the ordered weight. It will be included in the supply if hot-rolled and separately wrapped if cold-rolled. Note: possibility of supplying sandblasted drawn sections with length 2.8 ÷ 6.8 m (including the length+ tolerance).

DIMENSIONAL TOLERANCES: UNI EN 10277; UNI EN ISO 286; ASTM A108; BS 970		
Standard	IT10 - IT11 - BS970 Circularity deviation ≤ 50% of the Ø tolerance field.	
Extra standard	IT9 up to 72 mm (not guaranteed on products previously subjected to heat treatment). Circularity deviation \leq 50% of the Ø tolerance field.	

Note: full-length tolerances will have to be agreed upon at the order acquisition stage.

STRAIGHTNESS	
Standard	Camber ≤ 1‰ L
Extra Standard	Camber ≤ 0.5‰ L

ROUGHNESS Standard Ra ≤ 3.2 µm

Drawn round steel bars Revision: 07/2019 - Page 3 of 4

END APPEARANCE	
Standard	Shear or sawing machine cutting at both ends.
Extra Standard	Saw machine cutting and chamfering (max Ø 80 mm) on 1 or 2 ends; max. 10 mm with 30° - 45° chamfer.

SUPERFICIAL DEFECTS	
Standard	Class 2 EN 10277 (statistical)
Extra Standard	Class 2 - 3 EN 10277 with NDT 100% Class 2 is guaranteed for automatic steels.

Note: Note: semi-products can be previously subjected to US testing in accordance with standard EN 10308 Max Class 3

DECARBONISATION	
Standard	Max. 1% of the Ø, with a minimum equal to 0.2 mm.

NON-METALLIC INCLUSIONS	
Standard	Macro-purity at grade ≤ 2 as per S.E.P. 1584 standard. Micro-purity at grade ≤ 2,5 as per ASTM E 45 standard or with K method at the values of the EN 10083/06-1 standard, App E Macro-segregation ≤ C3-R2-S2 as per ASTM E 381 standard
Extra Standard	Through the vacuum degassing (VD) process it is possible to obtain macro-inclusions falling into grade 0 of the S.E.P. 1584 standard.

BANDING	
Standard	Maximum guaranteed banding as per Grade IV of the UNI 8449 standard.
Extra Standard	Through the vacuum degassing (VD) process, maximum guaranteed banding as per Grade III of the UNI 8449 standard.

AUSTENITE GRAIN REFINING FOR SPECIAL STEELS	
Standard	5 \div 8 austenite grain as per ASTM E112 or ISO 643 guaranteed. This grain size range is not guaranteed for general purpose structural steels, with the exception of the J2 types envisaged in the EN 10025-2 table.
Extra Standard	With extra standard process, 6 or finer austenite grain can be guaranteed.

Standard In accordance with the standardisation table mentioned in the order. On request, all steels can be produced with hardenability restricted to 2/3 of the H stan	MECHANICAL CHARACTERISTICS AND HARDENABILITY	
i.e. in the HL (lower 2/3) and HH (upper 2/3) types. Reference for Jominy test: EN ISO 642 standard.	dard band,	
Extra StandardIn accordance with Customer specification, to be evaluated at the order acceptance sta	ige.	

Drawn round steel bars

MAGNETIC RETENTIVITY

Standard

Not guaranteed

PACKAGING	
Standard	Anti-corrosion oiling 4 straps for 2.8÷5 m bundles. N° 4/6 straps for 5.5÷7.2 m. 1 Tag per bundle Certified metal lifting rings
Extra Standard	Peculiar conditions besides the previous ones, to be evaluated at the order acceptance stage. 2 tags, 1 at the front and 1 at the rear of the bundle Bundle packaging with polythene-jute cloth Plates at the ends Packaging in crates Polyester lifting belts Additional oiling and protective paper at the shipment stage.

HEAT TREATMENTS

Our products can be supplied with the following heat treatments: - Softening annealing +A - Spheroidising +AC - Stress-free annealing +SR

- Annealing for ferrite-pearlite structure +FP

- Normalising +N

- Shearability annealing +S - Hardening field annealing +TH

BUNDLE WEIGHT	
Standard	1,000 ÷ 1,600 kg
Extra standard	500 Kg

OTHER INFORMATION	
Hardness	Steels with hardness exceeding 245 HB must be previously annealed
Manufacturing times	30÷40 days
Product certificate	Compliant with EN 10204
Minimum batch size	5 tons.
Weight tolerance with respect with the ordered amount	± 20% up to 5 tons. ± 10% > 5 tons.